



DATA SHEET: Type Recelon

Compound of Polypropylene and LDPE (40%/60%).

PROPERTY	UNIT	VALUE
Melt index ASTM D 1238	gr/10 min. 2,16 kg/230oC	16
	gr/10 min. 2,16 kg/190oC	8,1
Density	G/cm/3	0,925
Colour	White, black, yellow, green and blue	
Melting temperature	oC	124 – 164
Manufacturing temperature	OC	190 – 230
Tensile yield strength	Mpa	25
Elongation at break	%	750
Flexural Modulus	Mpa	930
Shrinkage by injection moulding	%	1

APPLICATIONS:

Injection moulding

PACKING:

Big Bag approx. 1200 kg

Bulk, approx. 25 tons

NOTE:

To the best of our belief we hereby certify, that this product conforms to the relevant release specifications stated above.

All other warranties, including those as to fitness for purpose and merchantable quantity are specifically excluded.

RC Plast A/S
Gellerupvej 112
DK-6800 Varde

Tlf.: +45 75 22 52 77
www.rcplast.dk
varde@rcplast.dk